

B150 C63000

Chemical Properties

Element	Chemical Composition %
Copper (Cu)	Balance
Aluminium (Al)	9.0 - 11.0
Iron (Fe)	2.0 - 4.0
Manganese (Mn)	1.5
Nickel (Ni)	4.0 - 5.5
Silicon (Si)	0.25
Tin (Sn)	0.20
Zinc (Zn)	0.30

Physical Properties

Property	Value
Melting Point - Liquidus	1930 °F
Melting Point - Solidus	1895 °F
Density	0.274 lb/in ³ at 68°F
Specific Gravity	7.58
Electrical Resistivity	116.0 Ωs-cmil/ft @ 68 °F
Electrical Conductivity	7% IACS @ 68 °F
Thermal Conductivity	22.6 Btu ft/(hr ft ² °F) at 68 °F
Coefficient of Thermal Expansion	9.0 10 ⁻⁶ per °F (68-572 °F)
Specific Heat Capacity	0.09 Btu/lb °F at 68°F
Modulus of Elasticity in Tension	17500 ksi
Modulus of Rigidity	6400 ksi
Machinability Rating	30%

Room Temperature Tensile & Hardness Data

Form	Temper	Section Size (ins)	Tensile (ksi) min	Yield (ksi) min	Elongation in HD min	Brinell (3000 kg)
Rod	Hot or cold	up to 1.0	110	68	10	201 - 248
	Finished	to 2.0	110	60	10	201 - 248
		and to 3.0	105	55	10	187 - 241
	Heat	3.0 - 12.0	100	50	10	187 - 241
	Treated	12.0 Plus	80	40	17	148 - 178
Forging	Heat treated	-	85	42.5	10	201 - 248

Product Forms

Round Bar

Disclaimer

This data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.